

Data Sheet / Specification

Rockmat Type 6D

<u>Rockmat</u>	Type 6D
Fibre	coir
Fibre Content (%)	100%
Fibre Characteristics	untreated, natural
DIN / ISO Standard of ready produced blanket	
Tensile Strength EN ISO-10319	89,5kg-force per 25cm
Weights & Dimensions	
Width (meter)	1,20
Length (meter)	25
Area (square meter)	30
Weight per Roll (kg)	25
Weight / Total (gr./m²)	~ 800
Weight / Fibre (gr./m ²)	+/- 450
Blanket Thickness	8 – 10mm
<u>Functional Longevity</u>	
Functional Longevity F ³ -FIBRE	24 – 36 months
Functional Longevity WIRE MESH	approx. 12-15 years
Slope recommendation	upto 70°
<u>Wire Mesh</u>	
Type	acc. to DIN 1200 – 0,8mm wire
Size	25 x 25mm, hexagon
Weight	350gr. /m ²
Galvanized Coating	+/- 0,075mm
Break Resistance	350 – 500 N/mm ²
<u>Nettings & Thread</u>	
Bottom Netting Type	Light – PP
Bottom Netting Mesh Size	9 x 9 mm
Bottom Netting Weight	4,8 gr./m ²